

tenure[®]4G



REF TEN4000

Tenure[®]4G Dual Solvent Bonding Agent

CONTENTS:

- Tenure4G A Adhesive 6 ml **CE** 0044
- Tenure4G B Adhesive 6 ml **CE** 0044
- Tenure S Enhancer 6 ml **CE** 0044
- Tenure S Filled 3 ml **CE** 0044
- Etch 'N' Seal[®] 3 ml **CE**
- Dappen dishes, 2 pc. **(NM-D)**
- Syringe tips 18 G, 6 pc. **(NM-D)**
- Brush-tip handle **(NM-D)**
- Brush tips, 60 pc. **(NM-D)**
- All Surface Bonding Chart **(NM-D)**
- Instruction sheet **(NM-D)**

Do Not Refrigerate

Symbols Glossary available at:
www.denmat.com/symbols

dm
DenMat[®]

R_X ONLY



LOT

Den-Mat Holdings, LLC
1017 W. Central Avenue
Lompoc, CA 93436 USA



38°F
2°C

77°F
25°C



EC REP

MDSS GmbH
Schiffgraben 41
30175 Hannover, Germany



©2018 Den-Mat Holdings, LLC. All rights reserved. 750114900 R:3 06/18BI

4G Greater bond strength and sensitivity control, turn to Tenure®4G, DenMat's next generation of the popular Tenure MPB bonding system. Tenure4G is a 4th generation multi-purpose, self-cure adhesive system for bonding any resin restorative to all intraoral surfaces. Tenure4G's formulation contains added ethanol to reduce patient sensitivity. Additionally, it has shown improved bond strength to give you more confidence in your composite restorations, all the while maintaining the same ease and simplicity you are accustomed to.

CAUTION: Wear protective gloves while using this product.

CAUTION: Wear eye protection while using this product.

CAUTION: Tenure has not been studied in children, pregnant or breast-feeding women.

INSTRUCTIONS:

Enamel and Dentin

1. Remove all caries and/or establish margins of restoration.
2. Apply Etch 'N' Seal to the enamel and dentin for 10-15 seconds.
3. Rinse thoroughly and dry.
4. Mix equal drops of Tenure4G A and Tenure4G B into dappen dish.
Note: Recommended temperature when used is 70° F-77° F (21°-25° C).
5. Apply 4 to 6 coats to the tooth surfaces with brush or until glossy in appearance.
6. Allow to fully evaporate, 10-15 seconds.
7. Optional: Apply one thin coat of Tenure S to the surface and light cure.*
8. Proceed with restoration of choice.

*Tenure S Bond Enhancer is recommended for wetting purposes and acts as a final sealer. Tenure S Filled is recommended for direct composite restorations as it is more viscous.

Old Composite/Resin

1. Roughen or sandblast surface. Rinse and dry.
2. Proceed with steps 4-8.

Metals

1. Roughen or sandblast surface. Rinse and dry.
2. Proceed with steps 4-7.
3. Apply GoldLink®, Geristore®, or Infinity® and restoration of choice.

INDICATIONS FOR USE:

1. All routine direct and indirect resin composite bonding.
2. Porcelain, ceramic veneers, amalgams, precious and semi-precious metals bonding.
3. Indirect gold, porcelain and ceramic inlays and onlays bonding.
4. Desensitization of root or dentin prior to impressions and temporaries.
5. Preparation desensitization of crown prior to impression or temporaries.

STORAGE

Do not expose to temperatures exceeding 77° F (25° C).
Do not expose to direct sunlight.

SAFETY DATA SHEETS AVAILABLE AT www.denmat.com